



TECHNICAL DATA SHEET

Document No	CPA-TDS-GA 01
Release Date	10.10.2023
Revision Date	
Revision No	

MAXPOWERWRAP MACHINE STRETCH FILM

PRODUCT GENERAL SPECIFICATION:

PRODUCT CODE:	MW206551
PRODUCT DESCRIPTION:	MACHINE STRETCH 51 GA / 13 MICRON
MAIN USAGE:	PALLET PACKAGING
PRODUCT TYPE	HIGH PERFORMANCE MACHINE STRETCH FILM FOR SEMI AND FULL AUTOMATED WRAPPERS SEMI HIGH RETENTION SEMI STIFF TYPE HIGH PUNCTURE RESISTANCE PRE-STRETCHING ON WRAPPER 50-300%
MATERIAL	LLDPE (LINEAR LOW-DENSITY POLYETHYLENE)
DENSITY	0.918 g/cm ³
COLOR	TRANSPARENT
RECYCLABILITY	YES-100%
CLARITY	HIGH
CLING	INSIDE
CORE TYPE	PAPER- PRINTED
CORE INTERIOR DIAMETER	2.99 INCH / 76 mm

PHYSICAL VALUES

TEST	VALUE	TOLERANCE	TEST METHOD
FILM WIDTH	19.7 INCH – 50 CM	+, - 1,5mm	ISO 4591
FILM THICKNESS	51 GA – 13 MICRON	+, - 5%	ISO 4591 / ASTM E252
FILM LENGTH	6500 FT – 1981 MTS	+, - 5%	ISO 4591
NET FILM WEIGHT	25.9 POUND – 11.76 KG	+, - 5%	ISO 4591
CORE WEIGHT	2,24 POUND - 1.1 KG	+, - 10%	
ROLL GROSS WEIGHT	28.34 POUND – 12.86 KG		





MECHANICAL PROPERTIES

TEST	VALUE	TOLERANCE	TEST METHOD
TENSILE STRENGTH AT BREAK – Mpa (Longitudinal)	39	+, - 10 Mpa	ISO 527 / ASTM D882
TENSILE STRENGTH AT BREAK – Mpa ((Transverse)	12,8	+, - 10 Mpa	ISO 527 / ASTM D882
ELONGATION AT BREAK % (Longitudinal)	300	+, - 10%	ISO 527 / ASTM D882
ELONGATION AT BREAK % (Transverse)	400	+, - 10%	ISO 527 / ASTM D882
DART IMPACT - Kg	3,35	+, - 20%	ISO 7765 / ASTM D1790

PACKAGING

BOX	YES
PCS PER BOX	1
BOX DIMENSIONS	210*210*533 mm
ROLL BUBBLING COVERAGE	YES
PCS / PALLET (SKID)	
PALLET (SKID) DIMENSIONS	
SELF LIFE	12 MONTHS
STORAGE	DRY, 15-25 C

COMPARISON

LOWEST: 1

HIGHEST :5

	RETENTION FORCE	TENSILE STRENGTH MD	PUNCTURE RESISTANCE	TEAR RESISTANCE	CONSUMPTION PER PALLET
MAXPOWERWRAP 51 GA	5	4,5	4,5	4,5	5
REGULAR MACHINE STRETCH – 70 GA	2	3	3	3	2

This comparison made under at semi automated wrapper under the same pallet and working conditions.

This data may vary without any notice – the updated typical sheets can be forwarded at any time. Since many different factors may influence the products' performance, we recommend that you test the product for your application to make sure that it is fit for purpose. This information does not express or imply a performance guarantee in any way whatsoever. We remain at your disposal for any further information.





www.caspianpro.com.tr



info@caspianpro.com.tr



Adalet Mah. Manas Blv.
Folkart Towers
No: 47B/2601 Bayraklı/İzmir